



Appl. Serial No.: 09/737,109
Filed: December 14, 2000
Group Art Unit: 1771
Examiner: A. Wachtel
Atty. Docket No.: 72545-37

AMENDMENTS TO THE CLAIMS

1. (Previously Presented) A nonwoven filter media composite, comprising:
glass wool fibers essentially free of boron; and
chopped glass fibers essentially free of boron and having an average fiber diameter in the range of about 5.0 microns to 9.0 microns, the chopped glass fibers having more than about 10% by weight of aluminum oxide and more than about 20% by weight of calcium oxide, wherein said chopped glass fibers are interspersed throughout said glass wool fibers.
2. (Original) The filter media composite of claim 1, wherein said glass wool fibers contain less than about 0.2% by weight boron oxide.
3. (Original) The filter media composite of claim 1, wherein said chopped glass fibers contain less than 1.0% by weight boron oxide.
4. (Original) The filter media composite of claim 1, wherein said glass wool fibers have an average diameter between about 0.1 microns and about 5.0 microns.
5. (Original) The filter media composite of claim 4, wherein said glass wool fibers have an average diameter of between about 0.4 microns and about 1.0 microns.
6. (Original) The filter media composite of claim 1, wherein the length to diameter (l/d) of said glass wool fibers is between about 100 to about 10,000.
7. (Original) The filter media composite of claim 6, wherein the length to diameter (l/d) of said glass wool fibers is about 300.
8. (Original) The filter media composite of claim 1, wherein the chopped glass fibers have an average diameter of about 6.5 microns.
9. (Original) The filter media composite of claim 1, wherein the chopped glass fibers have an average length of between about a quarter of an inch to a half an inch.

10. (Original) The filter media composite of claim 1, wherein said composite further includes a binder.
11. (Original) The filter media composite of claim 10, wherein said binder is between about 2 and 10% by weight of said composite.
12. (Original) The filter media composite of claim 11, wherein said binder is between about 3 and 9% by weight of said composite.
13. (Original) The filter media composite of claim 10, wherein said binder is an styrene-acrylic binder.
14. (Original) The filter media composite of claim 1, wherein said composite further includes a water repellent.
15. (Original) The filter media composite of claim 14, wherein said water repellent is between about 0.01% and 5.0% by weight of said composite.
16. (Original) The filter media composite of claim 15, wherein said water repellent is between about 0.05% and about 3.0% by weight of said composite.
17. (Original) The filter media composite of claim 14, wherein said water repellent is a fluoroacrylate.
18. (Original) The filter media composite of claim 1, wherein said composite further includes a surfactant.
19. (Original) The filter media composite of claim 18, wherein said surfactant is between about $1.5 \times 10^{-5}\%$ and about 1.0% by weight of said composite.
20. (Original) The filter media composite of claim 18, wherein said surfactant is between about 5×10^{-5} and about 0.1% by weight of said composite.

21. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have between about 55% and about 65% SiO_2 by weight.
22. (Original) The filter media composite of claim 21, wherein said chopped glass fibers have between about 59% and about 60% SiO_2 by weight.
23. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have between about 10% and 15% Al_2O_3 by weight.
24. (Original) The filter media composite of claim 23, wherein said chopped glass fibers have about 13% Al_2O_3 by weight.
25. (Cancelled).
26. (Original) The filter media composite of claim 25, wherein said chopped glass fibers have less than about 0.6% boron by weight.
27. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have less than about 1% iron oxides by weight.
28. (Original) The filter media composite of claim 27, wherein said chopped glass fibers have less than about 0.5% iron oxides by weight.
29. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have less than about 2% sodium oxide by weight.
30. (Original) The filter media composite of claim 29, wherein said chopped glass fibers have less than about 1.0% sodium oxide by weight.
31. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have less than about 3.0% potassium oxide by weight.

32. (Original) The filter media composite of claim 31, wherein said chopped glass fibers have less than about 0.5% potassium oxide by weight.
33. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have between about 20% and about 25% calcium oxide by weight.
34. (Previously Presented) The filter media composite of claim 33, wherein said chopped glass fibers have between about 21% and about 23% calcium oxide by weight.
35. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have less than about 5% magnesium oxide by weight.
36. (Original) The filter media composite of claim 35, wherein said chopped glass fibers have less than about 4.0% magnesium oxide by weight.
37. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 70% SiO₂ by weight.
38. (Original) The filter media composite of claim 37, wherein said glass wool fibers have between about 62% and about 69% SiO₂ by weight.
39. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 7% Al₂O₃ by weight.
40. (Original) The filter media composite of claim 39, wherein said glass wool fibers have between about 2.5% and about 6.5% Al₂O₃ by weight.
41. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 0.5% iron oxides by weight.
42. (Original) The filter media composite of claim 41, wherein said glass wool fibers have less than about 0.02% iron oxides by weight.

43. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 0.2% boron by weight.
44. (Original) The filter media composite of claim 43, wherein said glass wool fibers have less than about 0.08% boron by weight.
45. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 15% sodium oxide by weight.
46. (Original) The filter media composite of claim 45, wherein said glass wool fibers have between about 8.5% and about 12.5% sodium oxide by weight.
47. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 7% potassium oxide by weight.
48. (Original) The filter media composite of claim 47, wherein said glass wool fibers have between about 2.5% and about 7.0% potassium oxide by weight.
49. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 10.0% calcium oxide by weight.
50. (Original) The filter media composite of claim 49, wherein said glass wool fibers have between about 4.0% and about 6.0% calcium oxide by weight.
51. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 5% magnesium oxide by weight.
52. (Original) The filter media composite of claim 51, wherein said glass wool fibers have between about 2.5% and about 5.0% magnesium oxide by weight.
53. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 10% barium oxide by weight.

54. (Original) The filter media composite of claim 53, wherein said glass wool fibers have between about 0% and about 9.5% barium oxide by weight.

55. (Original) The filter media composite of claim 1, wherein said glass wool fibers have less than about 5% zinc oxide by weight.

56. (Original) The filter media composite of claim 55, wherein said glass wool fibers have between about 0.5 and about 3.0% zinc oxide by weight.

57. (Original) The filter media composite of claim 1, wherein said chopped glass fibers have between about 55% and about 65% SiO_2 , between about 10% and 15% Al_2O_3 , between about 0% and less than about 1% boron, less than about 1% iron oxides, less than about 2.0% sodium oxide, less than about 3.0% potassium oxide, between about 20% and 25% calcium oxide and less than about 5% magnesium oxide by weight, and wherein said glass wool fibers have less than about 70% SiO_2 by weight, less than about 7% Al_2O_3 , less than about 0.5% iron oxides, less than about 0.2% boron, less than about 15% sodium oxide, less than about 7% potassium oxide, less than about 10.0% calcium oxide, less than about 5% magnesium oxide, less than about 10% barium oxide, and less than about 5% zinc oxide by weight.

58. (Original) The filter media composite of claim 57, wherein said chopped glass fibers make up between about 5% and about 40% of the total weight of said filter media composite.

59. (Currently Amended) The filter media composite of claim 1, wherein chopped glass fibers have between about 59% and about 60% SiO_2 , about 13% Al_2O_3 , less than about 0.6% boron, less than about 0.5% iron oxides, less than about 1.0% sodium oxide, less than about 0.5% potassium oxide, between about 21% and about 23% ~~sodium~~ calcium oxide, 4.0% magnesium oxide by weight, and said glass wool fibers have between about 62% and about 69% SiO_2 , between about 2.5% and about 6.5% Al_2O_3 , less than about 0.2% iron oxides, less than about 0.08% boron, between about 8.5% and about 12.5% sodium oxide, between about 2.5% and about 7.0% potassium oxide, between about 4.0% and about 6.0% calcium oxide, between

about 2.5% and about 5.0% magnesium oxide, between about 0% and about 9.5% barium oxide, and between about 0.5 and about 3.0% zinc oxide by weight.

60. (Original) The filter media composite of claim 59, wherein said chopped glass fibers make up between about 5% and about 40% of the total weight of said filter media composite.

61. (Original) The filter media composite of claim 1, wherein said chopped glass fibers make up between about 5% and about 40% of the total weight of said filter media composite.

62. (Original) The filter media composite of claim 1, wherein said chopped glass fibers make up between about 20% and about 25% of the total weight of said filter media composite.

63. (New) A nonwoven filter media composite, comprising:
glass wool fibers essentially free of boron; and
chopped glass fibers essentially free of boron and having an average fiber diameter in the range of about 5.0 microns to 9.0 microns, the chopped glass fibers being interspersed throughout the wool fibers;
wherein the filter media has a crease tensile strength value of at least about 2.5 lb/inch.

64. (New) The nonwoven filter media of claim 63, wherein crease tensile strength diminishes less than about 50% over a period of 48 hours.